

Denso Priming Solution

Brush or spray applied primer for large areas

Composition

Denso Priming Solution is comprised of petrolatum in hydrocarbon solvent.

Uses

Denso Priming Solution is used on large areas of substrate prior to the application of petrolatum tapes and compounds.

Service temperatures: -20°C to +60°C.

Characteristics

Denso Priming Solution is:

- suitable for brush or spray application, and
- easy to apply.

Surface Preparation

Surfaces must be clean, dry and free from rust, scale and non-adherent coatings by wire brushing to St2 or abrasive blast cleaning.

Application

Apply Denso Priming Solution evenly over the surface using a brush or roller to an average dry film thickness of 50 µm.

Application temperatures: -20°C to +55°C.

Cleaning solvent

Denso Priming Solution may be cleaned with white spirit or xylene.

Availability

Denso Priming Solution is available in 5 L tins or 25 L drums.

Storage conditions

Store all components upright in original packaging in a cool, dry, area. Keep away from heat, sparks and open flames.

Waste material

Please avoid or minimise waste wherever possible. Please do not discard waste material, including packaging, in the surrounding environment. Follow all relevant legislation for disposal.

Typical Properties

Viscosity (BS B4 cup at 25°C)	65 seconds
Flash Point	32°C
Specific gravity	0.9
Drying time	60 minutes
Surface coverage	9 m ² /L
VOC	<370 g/L
Solids	66% w/w

Important: Winn & Coales (Denso) Ltd pursue a policy to develop and continually improve all of our products and therefore the information given in this data sheet is intended as a general guide and does not constitute a warranty of specification. However, our sales personnel are committed to assist the user in establishing the suitability of the product for its intended purpose and additional specific information is available on request. Winn & Coales (Denso) Ltd operate a Quality Management System registered to BS EN ISO 9001 (BSI Certificate no. FM01548) and an Environmental Management System registered to BS EN 14001 (BSI Certificate 583748).