

Densoclad 40HT

Anti-corrosion tape for long-term corrosion protection of buried or immersed pipes and fittings

Composition

Densoclad 40HT is comprised of polymer modified bitumen coated onto a tough, plasticised PVC film. The bitumen compound is protected by a release paper, wider than the tape, which is discarded during application.

Uses

Densoclad 40HT is designed for the protection of small and medium diameter pipes, welded joints, bends and fittings. The combination of extremely conformable PVC backing and polymer bitumen compound ensures good contact with the metal substrate and excellent adhesion.

Service Temperature: -20°C to +75°C

Characteristics

Densoclad 40HT is:

- extremely conformable,
- suitable for hand or machine application,
- resistant to cathodic disbondment, and
- resistant to acid, alkali and salts.

Typical Properties

Total Thickness	1.05 mm	ASTM D1000
Backing Film Thickness	0.15 mm	ASTM D1000
Compound Thickness	0.90 mm	ASTM D1000
Weight	1.2 kg/m ²	
Breaking Strength	3.5 N/mm	ASTM D1000
Elongation at Break	200%	ASTM D1000
Tear strength	12 N	ASTM D1004
Adhesion (180° peel)		
to primed steel	3.5 N/mm	ASTM D1000
to self	3.5 N/mm	(24 hrs)
Impact Resistance (two layers)	2.5 Nm	ASTM G14
Dielectric Strength	20 kV/mm	ASTM D1000
Insulation Resistance	10 ⁶ MΩ	ASTM D257

Application

See *Instructions for Use* for further details

Primer: Denso Primer D

Densoclad 40HT is applied over Denso Primer D by wrapping spirally around the pipe with 55% overlap.

Application Temperature: +15°C to +50°C

Availability

Densoclad 40HT is available in 15 metre rolls,

- core diameter (internal): 76 mm
- 50 to 300 mm widths.

Other sizes may be available on request.

Storage conditions

Store in a cool and dry place in original packaging

Waste material

Please avoid or minimise waste wherever possible. Please do not discard waste material, including packaging, in the surrounding environment. Follow all relevant legislation for disposal.

Important: Winn & Coales (Denso) Ltd pursue a policy to develop and continually improve all of our products and therefore the information given in this data sheet is intended as a general guide and does not constitute a warranty of specification. However, our sales personnel are committed to assist the user in establishing the suitability of the product for its intended purpose and additional specific information is available on request. Winn & Coales (Denso) Ltd operate a Quality Management System registered to BS EN ISO 9001 (BSI Certificate no. FM01548) and an Environmental Management System registered to BS EN 14001 (BSI Certificate 583748).