

Denso Glass Outerwrap

Protective Fibreglass Outerwrap

Composition

Denso Glass Outerwrap is a fibreglass cloth wrap impregnated with a water activated resin.

Uses

Denso Glass Outerwrap offers excellent performance against abrasion, gouge, and impact to protect Denso anti-corrosion coating systems during and after installation. It is used as a protective outerwrap in applications involving soil-to-air, underwater, underground and aboveground pipes and piles. It is also used for a variety of other applications where additional mechanical protection is required.

Characteristics

Denso Glass Outerwrap:

- prevents damage to anti-corrosion coatings,
- resists water, acid, salts, and soil organics,
- resists hot and cold temperatures,
- has excellent abrasion, gouge and impact resistance,
- can be applied to dry, underwater or wet surfaces,
- contains no solvents,
- requires minimal surface preparation,
- is easy to apply with no mixing or messy clean up,
- is ready for immediate service,
- can be top-coated for aesthetics,
- provides a quick, long term protective coating, and
- is a CSA Z245.30 component.

Surface preparation

Surfaces must be clean and dry. Remove all loose, rust, scale and flaking coatings or other foreign matter by scraping, wire brushing, high pressure water washing or blast cleaning.

Application

See *Instructions for Use* for additional detail. Ensure your chosen Denso petrolatum tape or Viscotaq system is correctly installed following

product specific data sheet. For irregular surfaces such as valves, flanges, etc., may require the use of Densyl Mastic, Denso Profiling Mastic or ViscoMastic prior to product application to transition diameter variations. Refer to the product data sheets for these specific products for information on application and selection.

For application of the Denso Glass Outerwrap, use rubber gloves to remove the product from the hermetically sealed foiled pouch and soak in temperate water (salt or fresh) for 20 to 30 seconds. Remove from water and begin wrapping tightly, overlapping a recommended minimum 50%.

Proceed with a final temporary double layer of Denso Clear Outerwrap which shall be immediately applied over and in the same direction as the uncured Denso Glass Outerwrap. This allows all seams of the Denso Glass Outerwrap to lay out more smoothly and provides a tighter cured seal. If needed, once compressed, use the Denso Perforating tool or equivalent to puncture the Denso Clear Outerwrap to allow excess resin, moisture and CO₂ to escape during the reaction. The Denso Clear Outerwrap should be removed after approximately 15 to 30 minutes depending on temperature.

Availability

Tape width	Roll length	Rolls/carton	Approx. coverage with 50% overlap
75 mm	2.7 m	100	10.7 m ² /case
100 mm	9.0 m	40	18.4 m ² /case
200 mm	12.0 m	15	18.4 m ² /case

Additional sizes may be available on request.

Cleaning

Remove any resin immediately from any contaminated surface using a clean dry cloth. If a solvent is required, use xylene or dibasic ester or comparable solvent containing essentially no water.

Important: Winn & Coales (Denso) Ltd pursue a policy to develop and continually improve all of our products and therefore the information given in this data sheet is intended as a general guide and does not constitute a warranty of specification. However, our sales personnel are committed to assist the user in establishing the suitability of the product for its intended purpose and additional specific information is available on request. Winn & Coales (Denso) Ltd operate a Quality Management System registered to BS EN ISO 9001 (BSI Certificate no. FM01548) and an Environmental Management System registered to BS EN 14001 (BSI Certificate 583748).

Denso Glass Outerwrap

Storage

Shelf life is 24 months when stored in original packaging at 5°C to 32°C. Do not store in direct sunlight.

Waste material

Please make sure any unused product and any resin remaining in the foil pouch is fully cured before discarding as waste. Please avoid or minimise waste wherever possible. Please do not discard waste material, including packaging, in the surrounding environment. Follow all relevant legislation for disposal.

Typical Properties

Thickness	0.28 mm	
Flexural Strength	180 MPa	ASTM D790
Tensile Strength		
<i>Strength</i>	228 MPa	ASTM D3039
<i>Modulus</i>	16.5 GPa	
<i>Strain</i>	1.43%	
Tabor Abrasion		
<i>Wear index</i>	57.1 mg/1000 cycles	ASTM D4060-14
<i>Thickness loss (after 1000 cycles)</i>	75 microns	
<i>Initial thickness avg.</i>	0.86 mm	
Compression Strength	202 MPa	ASTM D695-15
Lap Shear Strength	12.1 MPa	ASTM D5868-01R14
Dielectric Strength	6300 V/mm	ASTM D149-09 (2013)
Impact Resistance	135 J	NACE SP 0394
Maximum service temperature	121°C	
Setting time		
@ 21°C	30 minutes	
@ 32°C	15 minutes	

Important: Winn & Coales (Denso) Ltd pursue a policy to develop and continually improve all of our products and therefore the information given in this data sheet is intended as a general guide and does not constitute a warranty of specification. However, our sales personnel are committed to assist the user in establishing the suitability of the product for its intended purpose and additional specific information is available on request. Winn & Coales (Denso) Ltd operate a Quality Management System registered to BS EN ISO 9001 (BSI Certificate no. FM01548) and an Environmental Management System registered to BS EN 14001 (BSI Certificate 583748).

Page 2 of 2

Revision date: 28/09/2023

WINN & COALES (DENSO) LTD
Denso House, 33-35 Chapel Road,
London, SE27 0TR
United Kingdom



TEL: +44 (0) 20 8670 7511
FAX: +44 (0) 20 8761 2456
WEB: www.denso.net
EMAIL: mail@denso.net